

Product Technical Information



Glazed bricks | crystal range

Wienerberger Code	Various
Production Plant	Panningen (Netherlands)
Manufacture	Extruded
Configuration	Perforated
Colour	Various
Appearance	Glazed/Smooth
Work Size (mm)	215 x 102.5 x 65
Pack Quantity	384
Individual Dry Brick Weight (kg)	2.4



Technical Properties to BS EN 771-1

Size Tolerance (Mean/Range)	T2/R1
Gross Dry Density (kg/m ³ /Tolerance)	1700 (D1)
Compressive Strength (N/mm ²)	≥50
Thermal Conductivity (W/(m·K)) λ _{10,dry,unit} value (EN 1745 tabulated: S1)	P=90% 0.55
Durability Designation	F2
Water Absorption (%)	≤2
Initial Rate of Water Absorption (kg/(m ² ·min))	Min. 0.0 Max. 0.5
Active Soluble Salts	S2
Reaction to Fire	Class A1

 **BIM OBJECTS** are available to download

GET IN TOUCH

- ☎ 0161 491 8200
- ✉ wbukmarketing@wienerberger.com
- 🌐 wienerberger.co.uk/glazed-bricks

Technical data correct at time of issue. Individual dry brick weights can vary and are for guidance only. Any questions regarding this data should be referred to the Wienerberger Technical Department. Due to the limitations of screen and print colour representation of product images it is advised that brick samples are viewed prior to ordering.

